

d	Flache	G	W ¹⁾	U ²⁾	d	Flache	G	W ¹⁾	U ²⁾
mm	cm ²	kg/m	cm ³	cm ² /m	mm	cm ²	kg/m	cm ³	cm ² /m
میلگرد فولادی (گرم نورد شده) برای مصارف عمومی طبق DIN EN 10060 چاپ فوریه 2004 و طبق DIN 1013 قسمت اول و دوم چاپ نوامبر 1978 و DIN 59130، چاپ دسامبر 1976									
10	0.785	0.617	0.098	314	115	104	81.5	149	3610
12	1.13	0.888	0.170	377	120	113	88.8	170	3770
13	1.33	1.04	0.216	408	125	123	96.3	192	3930
14	1.54	1.21	0.269	440	130	133	104	216	4080
15	1.77	1.39	0.331	471	135	143	112	242	4240
16	2.01	1.58	0.402	503	140	154	121	269	4400
18	2.54	2.00	0.573	565	145	165	130	300	4550
19	2.84	2.23	0.673	597	150	177	139	331	4710
20	3.14	2.47	0.785	628	155	189	148	366	4870
22	3.80	2.98	1.05	691	160	201	158	402	5030
24	4.52	3.55	1.36	754	165	214	168	441	5180
25	4.91	3.85	1.53	785	170	227	178	482	5340
26	5.31	4.17	1.73	817	175	241	189	526	5500
27	5.73	4.49	1.93	848	180	254	200	573	5650
28	6.16	4.83	2.16	880	190	284	223	673	5970
30	7.07	5.55	2.65	942	200	314	247	785	6280
32	8.04	6.31	3.22	1010	220	380	298	1045	6910
35	9.62	7.55	4.21	1100	250	491	385	1534	7850
36	10.2	7.99	4.58	1130	میلگرد فولادی (استاندارد نشده) ⁴⁾				
38	11.3	8.90	5.39	1190					
40	12.6	9.86	6.28	1260					
42	13.9	10.9	7.27	1320					
45	15.9	12.5	8.95	1410	8	0.503	0.395	0.050	251
48	18.1	14.2	10.9	1510	17	2.27	1.78	0.482	534
50	19.6	15.4	12.3	1570	21	3.46	2.72	0.909	660
52	21.2	16.7	13.8	1630	23	4.15	3.26	1.19	723
55	23.8	18.7	16.3	1730	31	7.55	5.92	2.92	974
60	28.3	22.2	21.2	1880	34	9.08	7.13	3.86	1070
63	31.2	24.5	24.5	1980	37	10.8	8.44	4.97	1160
65	33.2	26.0	27.0	2040	44	15.2	11.9	8.36	1380
70	38.5	30.2	33.7	2200	47	17.3	13.6	10.2	1480
73	41.9	32.9	38.2	2290	53	22.1	17.3	14.6	1670
75	44.2	34.7	41.4	2360	185	269	211	622	5810
80	50.3	39.5	50.3	2510	210	346	272	909	6600
85	56.7	44.5	60.3	2670	230	416	326	1194	7220
90	63.6	49.9	71.6	2830	240	452	355	1357	7540
95	70.9	55.6	84.2	2980	260	531	417	1726	8170
100	78.5	61.7	98.2	3140	270	573	450	1932	8480
105	84.6	68.0	114	3300	280	616	483	2155	8800
110	95.0	74.6	131	3460	290	661	519	2395	9110